

ORION

RECTIFIED POLISHED PORCELAIN

ORION

TECHNICAL STANDARDS

Description	ASTM	ANSI	Result
Water Absorption	C-373	≤ 3%	≤ 0.5%
Break Strength (lbs.)	C-648	≥ 250 lbs	Min. 300 lbs
Scratch Hardness	MOH's Scale	N/A	5
Chemical Resistance	C-650	Unaffected	Unaffected
Frost Resistance	C-1026	Resistant	Resistant
Group	C-1027	N/A	4
Minimum Bond Strength (PSI)	C-482	≥ 50 lbs	165
Shade and Texture Rating	V	N/A	V3
Coefficient of Friction/ Dry	C-1028	Varies	≥ 0.75
Coefficient of Friction/ Wet	C-1028	Varies	≥ 0.60

PRODUCT CHARACTERISTICS

- Polished Surface with Low Index of Repetitivity
- Rectified Mono-Caliber

APPLICATIONS

- Ideal Large Format for Commercial Applications

Roca

Roca

Roca Tile Group

LAUFEN

**UNITED STATES
CERAMIC TILE**

Incepa

4244 Mount Pleasant St. NW, Suite 100, North Canton, OH 44720 / (800) 321-0684 / www.rocatilegroup.com

RION



BLANCO



24 x 24 (23⁵/₈ x 23⁵/₈)
FM20960011




12 x 24 (11³/₄ x 23⁵/₈)
FM20957011

BEIGE




24 x 24 (23⁵/₈ x 23⁵/₈)
FM20960041



12 x 24 (11³/₄ x 23⁵/₈)
FM20957041

MARRON



24 x 24 (23⁵/₈ x 23⁵/₈)
FM20960251



12 x 24 (11³/₄ x 23⁵/₈)
FM20957251

ANTRACITA



24 x 24 (23⁵/₈ x 23⁵/₈)
FM20960311



12 x 24 (11³/₄ x 23⁵/₈)
FM20957311

24 x 24 Blanco and Antracita